

CLAIMS

1. A computer readable medium encoded with a program that, when executed on a polymer processing apparatus controller, performs a method comprising acts of:

(A) receiving a first input indicative of an amount of a polymeric material to be provided to a polymer processing space of a polymer processing apparatus; and

(B) automatically determining an amount of a blowing agent to be provided to the polymer processing space to form a foamed product based upon the amount of polymeric material.

2. The computer readable medium of claim 1, wherein the act (B) includes an act of automatically determining a plurality of amounts of the blowing agent, each of the plurality of amounts of the blowing agent including a sufficient amount of the blowing agent to form a microcellular foamed product.

3. The computer readable medium of claim 2, further comprising acts of:

(C) displaying the plurality of amounts of the blowing agent on a display device; and
(D) configuring, responsive to a second input selecting one of the plurality of amounts of the blowing agent, a blowing agent delivery system to provide the selected one of the plurality of amounts of the blowing agent to the polymer processing space.

4. The computer readable medium of claim 1, wherein the first input is indicative of the amount of polymeric material to be provided to the polymer processing space when forming a solid product, the method further comprising an act of:

(C) receiving a second input indicative of a desired weight reduction in the solid product;

wherein the act (B) includes an act of automatically determining the amount of the blowing agent to be provided to the polymer processing space to form a microcellular foamed product having the desired weight reduction relative to the solid product.

5. The computer readable medium of claim 4, further comprising an act of:

(D) determining a new amount of the polymeric material to be provided to the polymer processing space to form the microcellular foamed product having the desired weight reduction relative to the solid product.

6. The computer readable medium of claim 5, further comprising an act of:

(E) configuring a blowing agent delivery system to provide the amount of the blowing agent to the polymer processing space to form the microcellular foamed product having the desired weight reduction relative to the solid product.

5

7. The computer readable medium of claim 6, further comprising an act of:

(F) configuring the polymer processing apparatus to supply the new amount of the polymeric material to the polymer processing space.

10

8. The computer readable medium of claim 4, further comprising an act of:

(D) configuring a blowing agent delivery system to provide the amount of the blowing agent to the polymer processing space to form the microcellular foamed product having the desired weight reduction relative to the solid product.

15

9. The computer readable medium of claim 1, wherein the first input is indicative of the amount of polymeric material to be provided to the polymer processing space when forming a solid product, and wherein the act (B) includes an act of automatically determining a plurality of amounts of the blowing agent to be provided to the polymer processing space, each of the plurality of amounts of the blowing agent including a sufficient amount of the blowing agent to form a microcellular foamed product, the method further comprising an act of:

20

(C) displaying, on a display device, the plurality of amounts of the blowing agent along with an indication of a weight reduction in the microcellular foamed product relative to the solid product for each of the plurality of amounts of the blowing agent.

25

10. The computer readable medium of claim 9, wherein the method further comprises an act of:

30

(D) configuring, responsive to a second input selecting one of the plurality of amounts of the blowing agent, a blowing agent delivery system to provide the selected one of the plurality of amounts of the blowing agent to the polymer processing space.

11. The computer readable medium of claim 10, further comprising an act of:

09826603 040504
T05040 E0922860

(E) determining a new amount of the polymeric material to be provided to the polymer processing space to form the microcellular foamed product based upon the selected one of the plurality of amounts of the blowing agent.

5 12. The computer readable medium of claim 11, further comprising an act of:

(F) configuring the polymer processing apparatus to supply the new amount of the polymeric material to the polymer processing space.

10 13. The computer readable medium of claim 1, wherein the first input is indicative of a mass amount of the polymeric material to be provided to the polymer processing space, and wherein the act (B) includes an act of automatically determining the amount of the blowing agent to be provided to the polymer processing space to form a microcellular foamed product based upon the mass amount of the polymeric material.

15 14. The computer readable medium of claim 13, wherein the method further comprises an act of:

(C) receiving a second input indicative of a type of the blowing agent;

20 wherein the act (B) includes an act of automatically determining the amount of the blowing agent to be provided to the polymer processing space to form the microcellular foamed product based upon the mass amount of the polymeric material and the type of the blowing agent.

25 15. The computer readable medium of claim 13, wherein the method further comprises acts of:

(D) receiving a second input indicative of a type of the blowing agent; and

(E) receiving a third input indicative of a type of the polymeric material;

30 wherein the act (B) includes an act of automatically determining the amount of the blowing agent to be provided to the polymer processing space based upon the mass amount of the polymeric material, the type of the polymeric material, and the type of the blowing agent.

16. The computer readable medium of claim 1, wherein the first input is indicative of a mass amount of the polymeric material in a microcellular foamed product, and wherein the act (B) includes an act of automatically determining the amount of the blowing agent to

09826603-040501

be provided to the polymer processing space to form the microcellular foamed product based upon the mass amount of the polymeric material in the microcellular foamed product.

5 17. The computer readable medium of claim 16, wherein the method further comprises an act of:

(C) receiving a second input indicative of a type of the blowing agent;

10 wherein the act (B) includes an act of automatically determining the amount of the blowing agent to be provided to the polymer processing space based upon the mass amount of the polymeric material in the microcellular foamed product and the type of the blowing agent.

18. The computer readable medium of claim 16, wherein the method further comprises acts of:

(D) receiving a second input indicative of a type of the blowing agent; and

15 (E) receiving a third input indicative of a type of the polymeric material;

20 wherein the act (B) includes an act of automatically determining the amount of the blowing agent to be provided to the polymer processing space based upon the mass amount of the polymeric material in the microcellular foamed product, the type of the polymeric material, and the type of the blowing agent.

19. The computer readable medium of claim 1, wherein the first input is indicative of a volume amount of the polymeric material to be provided to the polymer processing space, the method further comprising an act of:

(C) receiving a second input indicative of a type of the polymeric material;

25 wherein the act (B) includes an act of automatically determining the amount of the blowing agent to be provided to the polymer processing space to form a microcellular foamed product based upon a mass amount of the polymeric material to be provided to the polymer processing space; and

30 wherein the mass amount of the polymeric material is determined based upon the type of the polymeric material, a material melt density of the type of the polymeric material, and the volume amount of the polymeric material.

20. The computer readable medium of claim 19, wherein the method further comprises an act of:

0932603-040501

(D) receiving a third input indicative of a type of the blowing agent;

wherein the act (B) includes an act of automatically determining the amount of the blowing agent to be provided to the polymer processing space to form the microcellular foamed product based upon the mass amount of the polymeric material to be provided to the polymer processing space and the type of the blowing agent.

21. The computer readable medium of claim 1, wherein:

the first input is indicative of a volume amount of the polymeric material to be provided to the polymer processing space;

wherein the act (B) includes an act of automatically determining the amount of the blowing agent to be provided to the polymer processing space to form a microcellular foamed product based upon a mass amount of the polymeric material to be provided to the polymer processing space; and

wherein the mass amount of the polymeric material is determined based upon a material melt density of the polymeric material, and the volume amount of the polymeric material.

22. The computer readable medium of claim 21, wherein the method further comprises an act of:

(C) receiving a second input indicative of a mass percentage of the blowing agent to be provided to the polymer processing space relative to the mass amount of the polymeric material to be provided to the polymer processing space; and

wherein the act (B) includes an act of automatically determining the amount of the blowing agent to be provided to the polymer processing space to form the microcellular foamed product based upon the mass amount of the polymeric material and the mass percentage of the blowing agent.

23. The computer readable medium of claim 22, wherein the method further comprises an act of:

(D) configuring a blowing agent delivery system to provide the amount of the blowing agent to the polymer processing space.

24. The computer readable medium of claim 23, wherein the blowing agent delivery system includes at least one valve through which the blowing agent is provided to the polymer processing space;

wherein the blowing agent delivery system provides a predetermined flow rate of the blowing agent to the at least one valve; and

wherein the act (D) includes an act of determining an open time of the at least one valve based upon the amount of the blowing agent to be provided to the polymer processing space and the predetermined flow rate.

25. The computer readable medium of claim 24, wherein the act (D) further includes an act of controlling the at least one valve according to the open time.

26. The computer readable medium of claim 23, wherein the blowing agent delivery system includes at least one valve through which the blowing agent is provided to the polymer processing space;

wherein the blowing agent delivery system provides a predetermined flow rate of the blowing agent to the at least one valve; and

wherein the act (D) includes an act of determining a position to which the at least one valve is opened based upon the amount of the blowing agent to be provided to the polymer processing space and the predetermined flow rate.

27. The computer readable medium of claim 23, wherein:

the polymer processing apparatus is an injection molding machine that includes a screw having a screw recovery time;

the blowing agent delivery system includes at least one valve; and

the act (D) includes an act of setting a flow rate of the blowing agent delivery system based upon the amount of blowing agent to be provided to the polymer processing space and the screw recovery time.

28. The computer readable medium of claim 23, wherein the blowing agent delivery system includes at least one valve having a valve open time during which the blowing agent flows through the at least one valve and into the polymer processing space, the method further comprising an act of:

(E) receiving a third input indicative of the valve open time;

09326603.040501

wherein the act (D) includes an act of setting a flow rate of the blowing agent delivery system based upon the amount of blowing agent to be provided to the polymer processing space and the valve open time.

5 29. The computer readable medium of claim 28, wherein the method further comprises acts of:

 (F) receiving a fourth input indicative of a valve opening condition of the at least one valve; and

 (G) controlling an opening of the at least one valve based upon the valve opening
10 condition.

 30. The computer readable medium of claim 28, wherein the polymer processing apparatus is one of an injection molding machine, a blow molding machine, and an extruder.

15 31. The computer readable medium of claim 28, further comprising an act of:
 (F) monitoring an actual flow rate of the blowing agent that is provided to the polymer processing space by the blowing agent delivery system.

 32. The computer readable medium of claim 28, further comprising an act of:
20 (F) receiving a fourth input indicative of an actual melt pressure of the polymeric material within the polymer processing space;

 wherein the act (D) includes an act of setting a pressure of the blowing agent to be provided to the polymer processing space by the blowing agent delivery system approximately 50-100 psi above the actual melt pressure of the polymeric material.

25 33. The computer readable medium of claim 28, further comprising an act of:
 (F) receiving a fourth input indicative of a desired melt pressure of the polymeric material within the polymer processing space;

 wherein the act (D) includes an act of setting a pressure of the blowing agent to be
30 provided to the polymer processing space by the blowing agent delivery system approximately 50-100 psi above the desired melt pressure of the polymeric material.

 34. The computer readable medium of claim 33, further comprising an act of:

09826603-040503
T05070 E0992860

(G) monitoring an actual pressure of the polymeric material within the polymer processing space.

35. The computer readable medium of claim 34, further comprising an act of:

5 (H) monitoring an actual pressure of the blowing agent that is provided to the polymer processing space by the blowing agent delivery system.

36. The computer readable medium of claim 35, further comprising an act of:

10 (I) providing an indication to a user of the polymer processing apparatus when one of the actual pressure of the polymeric material within the polymer processing space is not approximately equal to the desired melt pressure; and

the actual pressure of the blowing agent is more than approximately 100 psi above the desired melt pressure of the polymeric material.

15 37. The computer readable medium of claim 28, further comprising an act of:

(F) receiving a fourth input indicative of a desired melt pressure of the polymeric material within the polymer processing space;

20 wherein the act (D) includes an act of setting a pressure of the blowing agent to be provided to the polymer processing space by the blowing agent delivery system to a pressure that maintains a single-phase solution of the polymeric material and the blowing agent within the polymer processing space.

38. The computer readable medium of claim 28, further comprising an act of:

25 (F) receiving a fourth input indicative of an actual melt pressure of the polymeric material within the polymer processing space;

30 wherein the act (D) includes an act of setting a pressure of the blowing agent to be provided to the polymer processing space by the blowing agent delivery system to a pressure that maintains a single-phase solution of the polymeric material and the blowing agent within the polymer processing space.

39. The computer readable medium of claim 1, wherein the first input is indicative of a volume amount of the polymeric material to be provided to the polymer processing space, the method further comprising an act of:

wherein the act (B) includes an act of automatically determining the amount of the blowing agent to be provided to the polymer processing space to form the foamed product based upon the volume amount of the polymeric material to be provided to the polymer processing space, a material melt density of the polymeric material, and the mass percentage of the blowing agent.

(D) configuring a blowing agent delivery system to provide the amount of the blowing agent to the polymer processing space.

wherein the blowing agent delivery system provides a predetermined flow rate of the blowing agent to the at least one valve; and

42. The computer readable medium of claim 41, wherein the act (D) further includes an act of controlling the at least one valve according to the open time.

30 wherein the blowing agent delivery system provides a predetermined flow rate of the blowing agent to the at least one valve; and

wherein the act (D) includes an act of determining a position to which the at least one valve is opened based upon the amount of the blowing agent to be provided to the polymer processing space and the predetermined flow rate.

44. The computer readable medium of claim 40, wherein:
the polymer processing apparatus is an injection molding machine that includes a
screw having a screw recovery time;
5 the blowing agent delivery system includes at least one valve; and
the act (D) includes an act of setting a flow rate of the blowing agent delivery system
based upon the amount of blowing agent to be provided to the polymer processing space and
the screw recovery time.

10 45. The computer readable medium of claim 40, wherein the blowing agent
delivery system includes at least one valve having a valve open time during which the
blowing agent flows through the at least one valve and into the polymer processing space, the
method further comprising an act of:

(E) receiving a third input indicative of the valve open time;

15 wherein the act (D) includes an act of setting a flow rate of the blowing agent delivery
system based upon the amount of blowing agent to be provided to the polymer processing
space and the valve open time.

20 46. The computer readable medium of claim 45, wherein the method further
comprises acts of:

(F) receiving a fourth input indicative of a valve opening condition of the at least one
valve; and

(G) controlling an opening of the at least one valve based upon the valve opening
condition.

25 47. The computer readable medium of claim 45, wherein the polymer processing
apparatus is one of an injection molding machine, a blow molding machine, and an extruder.

48. The computer readable medium of claim 39, further comprising an act of:

30 (F) determining whether the amount of the blowing agent automatically determined
in act (B) is within a predetermined range of amounts of the blowing agent to form a
microcellular foamed product.

49. The computer readable medium of claim 48, further comprising an act of:

0982603-040501
T05040 E0992860

(G) providing an indication to a user of the polymer processing apparatus when it is determined in the act (F) that the amount of the blowing agent is not within the predetermined range of amounts of the blowing agent to form the microcellular foamed product.

5 50. The computer readable medium of claim 49, further comprising an act of:

 (H) requesting, responsive to the act (G) a new mass percentage of the blowing agent to be provided to the polymer processing space relative to the mass amount of the polymeric material to be provided to the polymer processing space when it is determined in the act (F) that the amount of the blowing agent is not within the predetermined range of amounts of the
10 blowing agent to form the microcellular foamed product.

 51. The computer readable medium of claim 49, further comprising an act of:

 (H) configuring a blowing agent delivery system to provide the amount of the blowing agent automatically determined in act (B) when it is determined in the act (F) that
15 the amount of the blowing agent is not within the predetermined range of amounts of the blowing agent to form the microcellular foamed product.

 52. The computer readable medium of claim 45, further comprising an act of:

 (F) monitoring an actual flow rate of the blowing agent that is provided to the
20 polymer processing space by the blowing agent delivery system.

 53. The computer readable medium of claim 52, further comprising acts of:

 (G) receiving a fourth input indicative of a desired melt pressure of the polymeric material within the polymer processing space; and

25 (H) monitoring an actual pressure of the polymeric material within the polymer processing space.

 54. The computer readable medium of claim 53, further comprising an act of:

 (I) providing an indication to a user of the polymer processing apparatus when the
30 actual pressure of the polymeric material within the polymer processing space is not approximately equal to the desired melt pressure.

 55. The computer readable medium of claim 1, wherein the polymer processing apparatus is one of an injection molding machine, a blow molding machine, and an extruder.

09826603-040504
T025040-00992866

56. A method comprising acts of:

(A) receiving a first input indicative of an amount of a polymeric material to be provided to a polymer processing space of a polymer processing apparatus; and

(B) automatically configuring, based upon the amount of polymeric material to be provided to the polymer processing space, a blowing agent delivery system to provide an amount of blowing agent to the polymer processing space to form a foamed product.

57. The method of claim 56, wherein the first input is indicative of the amount of polymeric material to be provided to the polymer processing space when forming a solid product, the method further comprising an act of:

(C) determining, based upon the amount of polymeric material to be provided to the polymer processing space, a plurality of amounts of the blowing agent to be provided to the polymer processing space, each of the plurality of amounts of the blowing agent including a sufficient amount of the blowing agent to form a microcellular foamed product;

(D) displaying, on a display device, the plurality of amounts of the blowing agent along with an indication of a weight reduction in the microcellular foamed product relative to the solid product for each of the plurality of amounts of the blowing agent; and

(E) receiving a second a second input selecting one of the plurality of amounts of the blowing agent;

wherein the act (B) includes an act of automatically configuring, responsive to the act (E), the blowing agent delivery system to provide the selected one of the plurality of amounts of the blowing agent to the polymer processing space.

58. The method of claim 56, wherein the first input is indicative of a volume amount of the polymeric material to be provided to the polymer processing space to form a microcellular foamed product, the method further comprising an act of:

(C) determining an amount of the blowing agent to be provided to the polymer processing space to form the microcellular foamed product based upon a material melt density of the polymeric material and the volume amount of the polymeric material;

wherein the act (B) includes an act of automatically configuring the blowing agent delivery system to provide the amount of the blowing agent determined in act (C).

59. The method of claim 58, wherein:

09826603.040501

the polymer processing apparatus is an injection molding machine that includes a screw having a screw recovery time;

the blowing agent delivery system includes at least one valve; and

the act (B) includes an act of automatically setting a flow rate of the blowing agent delivery system based upon the amount of blowing agent to be provided to the polymer processing space and the screw recovery time.

60. The method of claim 58, wherein the blowing agent delivery system includes at least one valve having a valve open time during which the blowing agent flows through the at least one valve and into the polymer processing space, the method further comprising an act of:

(D) receiving a second input indicative of the valve open time;

wherein the act (B) includes an act of automatically setting a flow rate of the blowing agent delivery system based upon the amount of blowing agent to be provided to the polymer processing space and the valve open time.

61. The method of claim 60, further comprising acts of:

(E) receiving a fourth input indicative of a valve opening condition of the at least one valve; and

(F) automatically controlling an opening of the at least one valve based upon the valve opening condition.

62. The method of claim 60, further comprising an act of:

(E) monitoring an actual flow rate of the blowing agent that is provided to the polymer processing space by the blowing agent delivery system.

63. The method of claim 60, further comprising an act of:

(E) receiving a fourth input indicative of an actual melt pressure of the polymeric material within the polymer processing space;
wherein the act (B) includes an act of automatically setting a pressure of the blowing agent to be provided to the polymer processing space by the blowing agent delivery system approximately 50-100 psi above the actual melt pressure of the polymeric material.

64. The method of claim 60, further comprising an act of:

(E) receiving a fourth input indicative of a desired melt pressure of the polymeric material within the polymer processing space;

wherein the act (B) includes an act of automatically setting a pressure of the blowing agent to be provided to the polymer processing space by the blowing agent delivery system approximately 50-100 psi above the desired melt pressure of the polymeric material.

65. The method of claim 64, further comprising an act of:

(F) monitoring an actual pressure of the polymeric material within the polymer processing space.

66. The method of claim 65, further comprising an act of:

(G) monitoring an actual pressure of the blowing agent that is provided to the polymer processing space by the blowing agent delivery system.

67. The method of claim 66, further comprising an act of:

(H) providing an indication to a user of the polymer processing apparatus when one of the actual pressure of the polymeric material within the polymer processing space is not approximately equal to the desired melt pressure; and the actual pressure of the blowing agent is more than approximately 100 psi above the desired melt pressure of the polymeric material.

68. The method of claim 60, further comprising an act of:

(E) receiving a fourth input indicative of a desired melt pressure of the polymeric material within the polymer processing space;

wherein the act (B) includes an act of automatically setting a pressure of the blowing agent to be provided to the polymer processing space by the blowing agent delivery system to a pressure that maintains a single-phase solution of the polymeric material and the blowing agent within the polymer processing space.

69. The method of claim 60, further comprising an act of:

(E) receiving a fourth input indicative of an actual melt pressure of the polymeric material within the polymer processing space;

wherein the act (B) includes an act of automatically setting a pressure of the blowing agent to be provided to the polymer processing space by the blowing agent delivery system to

09326603 "040501

a pressure that maintains a single-phase solution of the polymeric material and the blowing agent within the polymer processing space.

70. The method of claim 56, wherein the first input is indicative of a volume
5 amount of the polymeric material to be provided to the polymer processing space, the method further comprises acts of:

(C) receiving a second input indicative of a mass percentage of the blowing agent to be provided to the polymer processing space relative to a mass amount of the polymeric material to be provided to the polymer processing space;

10 (D) determining the mass amount of the polymeric material to be provided to the polymer processing space based upon the volume amount of the polymeric material and a material melt density of the polymeric material; and

(E) determining an amount of the blowing agent to be provided to the polymer processing space to form the foamed product based upon the mass amount of the polymeric material and the mass percentage of the blowing agent;
15

wherein the act (B) includes an act of automatically configuring the blowing agent delivery system to provide the amount of the blowing agent determined in act (E).

71. The method of claim 70, wherein:
20 the polymer processing apparatus is an injection molding machine that includes a screw having a screw recovery time;

the blowing agent delivery system includes at least one valve; and

the act (B) includes an act of automatically setting a flow rate of the blowing agent delivery system based upon the amount of blowing agent to be provided to the polymer
25 processing space and the screw recovery time.

72. The method of claim 70, wherein the blowing agent delivery system includes at least one valve having a valve open time during which the blowing agent flows through the at least one valve and into the polymer processing space, the method further comprising an
30 act of:

(D) receiving a second input indicative of the valve open time;

wherein the act (B) includes an act of automatically setting a flow rate of the blowing agent delivery system based upon the amount of blowing agent to be provided to the polymer processing space and the valve open time.

105049-09929603-040501

5 (H) automatically controlling an opening of the at least one valve based upon the valve opening condition.

(G) monitoring an actual flow rate of the blowing agent that is provided to the
10 polymer processing space by the blowing agent delivery system.

15 (H) monitoring an actual pressure of the polymeric material within the polymer processing space.

20 (A) providing an amount of polymeric material to a polymer processing space;
(B) introducing an amount of a blowing agent to the polymer processing space; and
(C) controlling the introduction of the amount of the blowing agent in act (B) to
provide a single-phase solution of the polymeric material and the blowing agent within the
polymer processing space.

(D) monitoring a melt pressure of the polymeric material within the polymer processing space;

78. The method of claim 77, further comprising an act of:

(E) providing the single-phase solution of the polymeric material and the blowing agent to a mold.

79. A controller for a blowing agent delivery system, comprising:

5 a first input to receive at least one input signal, the at least one input signal including a first input signal indicative of an amount of a polymeric material to be provided to a polymer processing space of a polymer processing apparatus;

a processor, coupled to the first input, that determines, based at least upon the first input signal, an amount of a blowing agent to be provided by the blowing agent delivery system to the polymer processing space to form a foamed product; and

10 a first output, coupled to the processor and the blowing agent delivery system, to provide a first output signal to the blowing agent delivery system that automatically configures the blowing agent delivery system to provide the amount of the blowing agent to the polymer processing space.

15 80. The controller of claim 79, further comprising:

an input device, coupled to the first input and the processor, to receive the at least one input signal and provide the at least one input signal to the processor; and

20 a communication device, coupled to the first output and the processor, to receive the first output signal from the processor and provide the first output signal to the blowing agent delivery system.

81. The controller of claim 80, further comprising:

a display device, coupled to the processor;

25 wherein the at least one input signal includes a first input signal and a second input signal, the first input signal being indicative of the amount of polymeric material to be provided to the polymer processing space when forming a solid product;

wherein the processor, responsive to receipt of the first input signal from the input device,

30 automatically determines a plurality of amounts of the blowing agent to be provided to the polymer processing space, each of the plurality of amounts of the blowing agent including a sufficient amount of the blowing agent to form a microcellular foamed product, and

displays the plurality of amounts of the blowing agent on the display device along with an indication of a weight reduction in the microcellular foamed product relative to the solid product for each of the plurality of amounts of the blowing agent; and

wherein the processor, responsive to receipt of the second input signal selecting one of the plurality of amounts of the blowing agent, provides the first output signal to the communication device to automatically configure the blowing agent delivery system to provide the selected one of the plurality of amounts of the blowing agent to the polymer processing space.

82. The controller of claim 80, wherein the first input signal is indicative of a volume amount of the polymeric material to be provided to the polymer processing space to form a microcellular foamed product;

wherein the processor, responsive to receipt of the first input signal from the input device,

automatically determines the amount of the blowing agent to be provided by the blowing agent delivery system to the polymer processing space to form the microcellular foamed product based upon a material melt density of the polymeric material and the volume amount of the polymeric material, and

provides the first output signal to the communication device to automatically configure the blowing agent delivery system to provide the amount of the blowing agent to the polymer processing space to form the microcellular foamed product.

83. The controller of claim 82, wherein the polymer processing apparatus is an injection molding machine that includes a screw having a screw recovery time;

wherein the blowing agent delivery system includes at least one valve;

wherein the processor, responsive to receipt of the first input signal from the input device,

automatically determines a mass flow rate of the blowing agent to be provided by the blowing agent delivery system based upon the amount of blowing agent to be provided to the polymer processing space and the screw recovery time, and

provides the first output signal to the communication device to automatically configure the blowing agent delivery system to provide the mass flow rate of the blowing agent automatically determined by the processor.

09825603.040501

84. The controller of claim 82, wherein the blowing agent delivery system includes at least one valve having a valve open time during which the blowing agent flows through the at least one valve and into the polymer processing space;

5 wherein the at least one input signal includes a second input signal indicative of the valve open time; and

wherein the processor, responsive to receipt of the second input signal from the input device,

10 automatically determines a mass flow rate of the blowing agent to be provided by the blowing agent delivery system based upon the amount of blowing agent to be provided to the polymer processing space and the valve open time, and

provides the first output signal to the communication device to automatically configure the blowing agent delivery system to provide the mass flow rate of the blowing agent automatically determined by the processor.

15 85. The controller of claim 84, further comprising:

a second output, coupled to the communication device and the blowing agent delivery system, to provide a second output signal;

20 wherein the at least one input signal includes a third input signal indicative of a valve opening condition of the at least one valve; and

wherein the processor, responsive to receipt of the third input signal, provides the second output signal to the communication device to automatically control the opening of the at least one valve based upon the valve opening condition.

25 86. The controller of claim 85, wherein the at least one input signal includes a fourth input signal indicative of a desired melt pressure of the polymeric material within the polymer processing space;

30 wherein the first output signal automatically configures the blowing agent delivery system to provide the amount of the blowing agent to the polymer processing space at a pressure approximately 50-100 psi above the desired melt pressure of the polymeric material.

87. The controller of claim 86, wherein the polymer processing apparatus is an injection molding machine having a screw and a screw back pressure regulator, the controller further comprising:

a third output, coupled to the communication device and the screw back pressure regulator, to provide a third output signal;

wherein the processor, responsive to the fourth input signal, provides the third output signal to the communication device to maintain the polymeric material at the desired melt pressure.

88. The controller of claim 87, further comprising:

a second input, coupled to the communication device, to receive a first pressure signal indicative of an actual melt pressure of the polymeric material within the polymer processing space and provide the first pressure signal to the processor;

a third input, coupled to the communication device, to receive a second pressure signal indicative of an actual pressure of the blowing agent delivered to the polymer processing space and provide the second pressure signal to the processor;

wherein the processor monitors the first and second pressure signals, and provides an indication to a user of the polymer processing apparatus when one of

the actual melt pressure of the polymeric material within the polymer processing space is not approximately equal to the desired melt pressure; and

the actual pressure of the blowing agent is more than approximately 100 psi above the desired melt pressure of the polymeric material.

89. The controller of claim 84, wherein the at least one input signal includes a third input signal indicative of a desired melt pressure of the polymeric material within the polymer processing space;

wherein the first output signal automatically configures the blowing agent delivery system to provide the amount of the blowing agent at a pressure that maintains a single-phase solution of the polymeric material and the blowing agent within the polymer processing space.

90. The controller of claim 84, further comprising:

a second input, coupled to the communication device, to receive a first pressure signal indicative of an actual melt pressure of the polymeric material within the polymer processing space;

wherein the first output signal automatically configures the blowing agent delivery system to provide the amount of the blowing agent to the polymer processing space at a pressure approximately 50-100 psi above the actual melt pressure of the polymeric material.

5 91. The controller of claim 80, wherein the first input signal is indicative of a volume amount of the polymeric material to be provided to the polymer processing space; wherein the at least one input signal includes a second input signal indicative of a mass percentage of the blowing agent to be provided to the polymer processing space relative to a mass amount of the polymeric material to be provided to the polymer processing space; and

10 wherein the processor, responsive to receipt of the first and second input signals from the input device,

 automatically determines the amount the blowing agent to be provided to the polymer processing space to form the foamed product based upon the volume amount of the polymeric material and the mass percentage of the blowing agent, and

 provides the first output signal to the communication device to automatically configure the blowing agent delivery system to provide the amount of the blowing agent to the polymer processing space to form the foamed product.

15 92. The controller of claim 91, wherein the polymer processing apparatus is an injection molding machine that includes a screw having a screw recovery time;

 wherein the blowing agent delivery system includes at least one valve;

 wherein the processor, responsive to receipt of the first and second input signals from the input device,

25 automatically determines a mass flow rate of the blowing agent to be provided by the blowing agent delivery system based upon the amount of blowing agent to be provided to the polymer processing space and the screw recovery time, and

 provides the first output signal to the communication device to automatically configure the blowing agent delivery system to provide the mass flow rate of the blowing agent automatically determined by the processor.

30 93. The controller of claim 91, wherein the blowing agent delivery system includes at least one valve having a valve open time during which the blowing agent flows through the at least one valve and into the polymer processing space;

09826603.040501

wherein the at least one input signal includes a third input signal indicative of the valve open time; and

wherein the processor, responsive to receipt of the third input signal from the input device,

5 automatically determines a mass flow rate of the blowing agent to be provided by the blowing agent delivery system based upon the amount of blowing agent to be provided to the polymer processing space and the valve open time, and

provides the first output signal to the communication device to automatically configure the blowing agent delivery system to provide the mass flow rate of the blowing agent automatically determined by the processor.

94. The controller of claim 93, further comprising:

a second output, coupled to the communication device and the blowing agent delivery system, to provide a second output signal;

15 wherein the at least one input signal includes a fourth input signal indicative of a valve opening condition of the at least one valve; and

wherein the processor, responsive to receipt of the fourth input signal, provides the second output signal to the communication device to automatically control the opening of the at least one valve based upon the valve opening condition.

95. The controller of claim 94, wherein the at least one input signal includes a fifth input signal indicative of a desired melt pressure of the polymeric material within the polymer processing space;

20 wherein the first output signal automatically configures the blowing agent delivery system to provide the amount of the blowing agent to the polymer processing space at a pressure approximately 50-100 psi above the desired melt pressure of the polymeric material.

96. The controller of claim 95, wherein the polymer processing apparatus is an injection molding machine having a screw and a screw back pressure regulator, the controller further comprising:

30 a third output, coupled to the communication device and the screw back pressure regulator, to provide a third output signal;

09825603-040501

wherein the processor, responsive to the fifth input signal, provides the third output signal to the communication device to maintain the polymeric material at the desired melt pressure.

5 97. The controller of claim 93, further comprising:

 a second input, coupled to the communication device, to receive a first pressure signal indicative of an actual melt pressure of the polymeric material within the polymer processing space and provide the first pressure signal to the processor;

 a third input, coupled to the communication device, to receive a second pressure
10 signal indicative of an actual pressure of the blowing agent delivered to the polymer processing space and provide the second pressure signal to the processor;

 wherein the processor monitors the first and second pressure signals, and provides an indication to a user of the polymer processing apparatus when one of

 the actual melt pressure of the polymeric material within the polymer
15 processing space is not approximately equal to the desired melt pressure; and

 the actual pressure of the blowing agent is more than approximately 100 psi above the desired melt pressure of the polymeric material.

20 98. The controller of claim 93, wherein the at least one input signal includes a fourth input signal indicative of a desired melt pressure of the polymeric material within the polymer processing space;

 wherein the first output signal automatically configures the blowing agent delivery system to provide the amount of the blowing agent at a pressure that maintains a single-phase solution of the polymeric material and the blowing agent within the polymer processing
25 space.

 99. The controller of claim 93, further comprising:

 a second input, coupled to the communication device, to receive a first pressure signal indicative of an actual melt pressure of the polymeric material within the polymer processing
30 space;

 wherein the first output signal automatically configures the blowing agent delivery system to provide the amount of the blowing agent to the polymer processing space at a pressure approximately 50-100 psi above the actual melt pressure of the polymeric material.

0982663-04504
T05040-80992360